TYGON E-LEI

The only choice for phthalate-free flexible tubing.

Non-DEHP Tubing for Laboratory, Food & Beverage, and Biopharmaceutical Applications

Taking a proactive approach to increased corporate social responsibility, Saint-Gobain has significantly reformulated Tygon® Long Flexible Life (LFL) tubing. The new Tygon® E-LFL tubing has benefits of increased sustainability and safety for the environment and end users and reduced risk, liability, and complexity for businesses. The new Tygon® E-LFL non-DEHP tubing is our best performing peristaltic pump tubing and has no industry equivalent. Tygon® E-LFL has been tested rigorously to ensure that it meets the same physical standards, including 1,000 hours of peristaltic pump tubing life at 0 psi back pressure, low particulate spallation and chemical resistance as the old Tygon® LFL tubing.

Tygon® Tubing Provides Optimal Peristaltic Pump Performance

Crystal-clear Tygon® E-LFL tubing is formulated specifically for use in peristaltic pump applications. The new Tygon® E-LFL non-DEHP tubing has even longer pump life not only at 0 psi but also at back pressure of up to 25 psi. The peristaltic pump life performance at different back pressures is shown on the back page. With its superior flex life characteristics, Tygon® E-LFL tubing reduces production downtime due to pump tubing failure. Our tests demonstrated reduced particle spallation, which eliminates the need for frequent downstream filter replacement and diminishes the risk of sensitive-fluid contamination. This is critical in several applications, such as pharmaceutical, high purity chemicals, cosmetics and food.

Various Benefits of Using Tygon® Long Flexible Life Tubing

The non-aging and broad chemical resistance properties of Tygon® E-LFL enable users to utilize the new tubing for transferring chemicals, cleaning agents and bactericides without danger of corrosion (as with metals) or oxidation (as with rubber). Tygon® E-LFL is safe and non-toxic and can be sterilized through conventional autoclave methods (steam 30 minutes at 15 psi), making it an excellent choice for high purity applications. It can be produced in up to a 6" (15.6 cm) inside diameter, ideal for bulk transfer applications.



Tygon® E-LFL Features/Benefits

- Longest flex life of any clear Tygon® tubing, reduces downtime due to pump failure
- Broad chemical resistance Excellent for laboratory applications
- Can be autoclave Suitable for high purity applications
- Extremely low particle spallation Reliable for sensitive-fluid applications
- Meets USP Class VI, ISO 10993 and FDA criteria
- · Contains no BPA or phthalates

Typical Applications

- Wide range of liquid transfer in labs
- Production filtration and fermentation
- Food & Beverage and cosmetic processing
- Biopharmaceutical
- Surfactant delivery
- · Flavor and vitamin concentrate dispensing
- · Printing ink transfer
- Highly viscous fluid transfer
- Drum and tank drainage
- · Shear-sensitive fluid transfer



www.pumptubing.com
TECHNICAL DATA
ANALYSIS COMPARISON

TYGON® E-LFL

www.labpure.com www.biopharm.saint-gobain.com www.processsystems.saint-gobain.com

Typical Physical Properties

Property	ASTM Method	TYGON® E-LFL Value or Rating		
Durometer Hardness Shore A, 15 Sec	D2240	56		
Tensile Strength, psi (MPa)	D412	1,800 (12.4)		
Ultimate Elongation, %	D412	400		
Tensile Stress, @ 100% psi (MPa) @ 200% psi (MPa)	D412	550 (3.8) 950 (6.6)		
Tear Resistance, lb-f/inch (kN/m)	D1004	184 (32.2)		
Compression Set Constant Deflection, % @ 158°F (70°C) for 22 hrs.	D395	68		
Brittleness by Impact Temp., °F (°C)	D746	-51 (-46)		
Specific Gravity	D792	1.17		
Water Absorption, % 24 hrs. @ 23°C	D570	0.20		
Maximum Recommended Operating Temp., °F (°C)	_	165 (74)		
Low Temp. Flexibility, °F (°C)	D380	-67 (-55)		
Tensile Set, %	D412	54		
Color	_	Clear		

More sizes available upon request.

Peristaltic Pump Tubing Life

The table below illustrates hours until failure of 1/4" ID x 3/8" OD tubing for 0, 10 and 15 psi and 1/4" ID x 7/16" OD tubing for 25 psi. In each case, a 3-roller pump head was utilized operating at 600 rpm under room temperature (73° F). Tubing failure is measured in hours of use prior to rupture.



The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.

TYGON® E-LFL Inventoried Sizes

Saint-Gobain	I.D. O.D.			0.D.		Wall Thickness		Length		Minimum Bend Radius		Maximum Working Pressure		Vacuum Rating mm of Mercury at	
Part Number			In. mm		Ft. m		In. mm		psi at bars at 73°F 23°C		73°F 23°C				
AVX42003	1/16	1.6	3/16	4.8	1/16	1.6	25	7.62	1/4	6.4	50	3.5	29.9	760	
AVX42007	1/8	3.2	1/4	6.4	1/16	1.6	25	7.62	1/2	12.7	34	2.3	29.9	760	
AVX42012	3/16	4.8	5/16	7.9	1/16	1.6	25	7.62	3/4	19.0	25	1.7	29.9	760	
AVX42017	1/4	6.4	3/8	9.5	1/16	1.6	25	7.62	1	25.4	20	1.4	15.0	381	
AVX42019	1/4	6.4	1/2	12.7	1/8	3.2	25	7.62	3/4	19.0	35	2.4	29.9	760	
AVX42022	5/16	7.9	7/16	11.1	1/16	1.6	25	7.62	1-1/4	31.75	16	1.1	10.0	254	
AVX42029	3/8	9.5	5/8	15.9	1/8	3.2	25	7.62	1	25.4	25	1.7	29.9	760	
AVX42038	1/2	12.7	3/4	19.0	1/8	3.2	25	7.62	1-1/2	38.1	20	1.4	20.0	508	
AVX06057	3/4	19.0	1-1/4	31.75	1/4	6.4	10	3.04	1-3/4	44.4	24	1.7	29.9	760	
AVX06064	1 C	25.4	1-3/8	34.9	3/16	4.8	10	3.04	3-1/4	82.5	15	1.0	5.0	127	

Working pressures are calculated at a 1:5 ratio relative to burst pressure using ASTM D1599.



Saint-Gobain Performance Plastics

2664 Gilchrist Road Akron, OH 44305 Tel: (800) 798-1554 Tel: (330) 798-9240 Fax: (330) 798-6968 TYGON® is a registered trademark.



IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics tubing for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubing in any particular application.

For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.

Saint-Gobain Performance Plastics Corporation assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.