# ND 100-65 Medical Tubing

# **Medical Products**

## From the ND Experts: The next generation in non-DEHP tubing

#### Features/Benefits

- Crystal clear for easy visualization of fluid flow
- Ideal for contact with bodily fluids
- Non-wetting surface permits complete drainage
- Meets USP Class VI criteria
- REACH compliant
- Withstands EtO, gas and gamma sterilization

#### **Typical Applications**

- Minimally invasive devices
- Blood and IV solutions
- Dialysis equipment
- Wound drainage
- Inhalation equipment
- Chemotherapy drug delivery
- Kidney dialysis pumps
- Peristaltic pumps
- Catheters

#### Plasticizer

• TOTM

# TYGON<sup>®</sup> ND 100-65 Tubing

TYGON<sup>®</sup> ND-100-65, one of the medical industry's first non-DEHP tubing offerings, has been formulated specifically to meet the demanding challenges of applications such as dialysis, chemotherapy drug delivery and minimally invasive surgeries.

### Characteristics

From open heart surgery to dialysis, ND 100-65 tubing has been specially formulated for medical device manufacturers that require a non-DEHP plasticized material. ND 100-65 sets the new standard for performance and durability in blood contact applications.

Based upon a unique chemistry developed by Saint-Goain, TYGON<sup>®</sup> ND Series tubing was formulated to be Registration, Evaluation, Authorization and restriction of CHemical substances (REACH) compliant for DEHP. To ensure compliance, every individual compound lot is tested to ensure DEHP levels are <1000 ppm. During the extrusion process, individual product dimensions are maintained and monitored through in-line micrometers and off-line verification with computerized imaging equipment.

Consistent with many medical tubing requirements, ND-100-65 material can be effectively bonded/welded using the following methods: heat, electronic (RF)/ultrasonic, solvent and adhesive. Factors to be considered when selecting the components include: security of the bond required, effect on the integrity of the materials to be joined and presence of residues or extractables that may affect biocompatibility. When bonding procedures are not used, mechanical clamps are recommended to provide secure attachment.

#### **Biocompatibility**

TYGON<sup>®</sup> ND 100-65 is made from a biocompatible non-DEHP polymer material developed specifically for blood contact medical device needs. It meets USP Class VI, ISO 10993, European Pharmacopoeia 3.1.1.2 and European REACH requirements. It is also non-hemolytic and non-pyrogenic.



**PERFORMANCE PLASTICS** 

Tel.: +52 (55) 6273-4046 / 6273-4048 / 2465-1016

# TYGON<sup>®</sup> ND 100-65 Manufactured Sizes and Pressures

Part Number	I.D. (inches)	O.D. inches (inches)	Wall Thickness (inches)	Length (feet)	Minimum Bend Radius (inches)	Max. Suggested Working Pressure at 73°F (psi)*	Vacuum Rating In. of Mercury at 73°F
ADF00001	1/32	3/32	1/32	50	1/8	100	29.9
ADF00002	1/16	1/8	1/32	50	1/4	55	29.9
ADF00003	1/16	3/16	1/16	50	1/8	100	29.9
ADF00004	3/32	5/32	1/32	50	3/8	40	29.9
ADF00005	3/32	7/32	1/16	50	1/4	70	29.9
ADF00006	1/8	3/16	1/32	50	1/2	30	25
ADF00007	1/8	1/4	1/16	50	3/8	55	29.9
ADF00009	5/32	7/32	1/32	50	3/4	25	15
ADF00010	5/32	9/32	1/16	50	1/2	45	29.9
ADF00011	3/16	1/4	1/32	50		20	10
ADF00012	3/16	5/16	1/16	50	5/8	40	29.9
ADF00012	3/16	3/8	3/32	50	1/8	55	29.9
ADF00013	3/16	7/16	1/8	50	3/8	70	29.9
ADF00014	1/4	5/16	1/32	50	1-5/8	18	5
ADF00018 ADF00017	1/4	3/8	1/32	50	1-578	30	25
ADF00017 ADF00018	1/4	7/16	3/32	50	3/4	45	
							29.9
ADF00019	1/4	1/2	1/8	50	5/8	55	29.9
ADF00022	5/16	7/16	1/16	50	1-3/8	25	15
ADF00023	5/16	1/2	3/32	50	1	35	29.9
ADF00024	5/16	9/16	1/8	50	7/8	45	29.9
ADF00027	3/8	1/2	1/16	50	1-3/4	20	10
ADF00028	3/8	9/16	3/32	50	1-3/8	30	25
ADF00029	3/8	5/8	1/8	50	1-1/8	40	29.9
ADF00032	7/16	9/16	1/16	50	2-1/4	20	8
ADF00033	7/16	5/8	3/32	50	1-3/4	25	18
ADF00034	7/16	11/16	1/8	50	1-3/8	35	29.9
ADF00036	1/2	5/8	1/16	50	2-7/8	18	6
ADF00037	1/2	11/16	3/32	50	2-1/8	25	15
ADF00038	1/2	3/4	1/8	50	1-3/4	30	25
ADF00041	9/16	3/4	3/32	50	2-1/2	20	10
ADF00045	5/8	13/16	3/32	50	3	20	9
ADF00046	5/8	7/8	1/8	50	2-3/8	25	15
ADF00047	5/8	15/16	5/32	50	2	30	25
ADF00053	3/4	40	1/8	50	3-1/4	20	10
ADF00059	7/8	1-1/8	1/8	50	4-1/8	20	8
ADF00062	1 1	1-1/4	1/8	50	5-1/8	18	5
ADF02002	1/16	1/8	1/32	100	1/4	55	29.9
ADF02003	1/16	3/16	1/16	100	1/8	100	29.9
ADF02004	3/32	5/32	1/32	100	3/8	40	29.9
ADF02006	1/8	3/16	1/32	100	1/2	30	25
ADF02007	1/8	1/4	1/16	100	3/8	55	29.9
ADF02011	3/16	1/4	1/32	100	1	20	10
ADF02012	3/16	5/16	1/16	100	5/8	40	29.9
ADF02017	1/4	3/8	1/16	100		30	25
ADF02018	1/4	7/16	3/32	100	3/4	45	29.9
ADF02022	5/16	7/16	1/16	100	1-3/8	25	15
ADF02027	3/8	1/2	1/16	100	1-3/4	20	10
ADF02028	3/8	9/16	3/32	100	1-3/8	30	25
ADF02020	3/8	5/8	1/8	100	1-1/8	40	29.9
ADF02025	1/2	11/16	3/32	100	2-1/8	25	15
ADF02038	1/2	3/4	1/8	100	1-3/4	30	25

# TYGON<sup>®</sup> ND 100-65 Typical Physical Properties

Property Color Color	ASTM Method	Value or Rating 65	
Durometer Hardness, Shore A, 15 sec.	D2240		
Color	$\sim \sim \sim \sim$	Clear	
Tensile Strength, psi (MPa)	D412	2,075 (14.3)	
Ultimate Elongation, %	D412	415	
Tear Resistance, lb-f/inch (kN/m)	D1004	185 (32.4)	
Specific Gravity	D792	1.19	
Water Absorption, % 24 hrs. @ 23°0	C D570	0.12	
Compression Set, Constant Deflection, % @ 158°F (70°C) for 22 hrs.	D395	60	
Maximum Recommended Operating Temp.,°F (°C)		165 (74)	
Brittleness by Impact Temp., °F (°C	) D746	-44 (-42)	
Tensile Modulus, @ 100% Elongation, psi (MPa)	D412	817 (5.6)	

Unless otherwise noted, all tests were conducted at room temperature ( $73^{\circ}$ F). Values shown were determined on 0.075" thick extruded strip or 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

# TYGON<sup>®</sup> ND 100-65 Characteristics

The biocompatibility of TYGON' ND 100-65 has been tested and found to be non-toxic in the following test protocols:

ISO 10993 – Cytotoxicity	Pass	
ISO 10993 – Genotoxicity	Pass	
ISO 10993 – In Vitro Platelet Aggregation	Pass	
ISO 10993 – Irritation/Sensitization	Pass	
ISO 10993 – Unactivated Partial Thromboplastin Time Assay	Pass	
USP Class VI	Pass	
USP Physicochemical Testing/Plastics	Pass	
USP Pyrogens	Pass	
USP – Chromogenic Testing	Pass	
USP - Chromogenic Validation		
USP Physicochemical Testing/Elastomeric Closures		
C3a Complement Activation Assay		
Hemocompatibility	Pass	
European Pharmacopoeia 3.1.1.2	Pass	

# **Sterilization Methods**

Autoclavable	Yes	
Gas	Yes	
Radiation	Yes (2.5 Mrad)	

The values listed for working and burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.

TYGON<sup>®</sup> tubing is not intended for use as an implant material.

Saint-Gobain Non-DEHP tubing contains DEHP levels of <1000 ppm.

#### TYGON<sup>®</sup> is a registered trademark.



#### Saint-Gobain Performance Plastics 2664 Gilchrist Road

Akron, OH 44305 Tel: 800-798-1554 Tel: (330) 798-9240 Fax: (330) 798-6968 **IMPORTANT:** It is the user's responsibility to ensure the suitability and safety of Saint-Cobain Performance Plastics tubing for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubin in any particular application.

For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.

Saint-Gobain Performance Plastics Corporation assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.

